USER'S GUIDE ALIS 579



SUITABLE FOR ALL TYPES OF WOOD*

*Please allow cedar to age a minimum of 6 months before applying the oil.

Considering the ecological composition of our products, we recommend cleaning only using GLOUROS 1806. Any other cleaning or surface preparation product could hinder proper oil adhesion.

SURFACE PREPARATION

The wood must be completely dry, dust free and nonsealed. We recommend refreshing the oxidized surface by sanding the wood with a 100 grit sanding paper. Apply at temperature of at least 10°C and make sure the temperature remains over 10°C for at least 8 hours after application.

OIL APPLICATION

1st COAT

Stir well with a stick to evenly mix the colour pigments in the oil. Apply the stain on a small surface to confirm your colour choice. Apply the coat with a brush, spray gun, applicator pad or with a roller just enough to saturate the wood. Let the surface absorb the oil for about 5 minutes then spread out the surface with a brush and make sure the surface is uniform. Wait about 18 hours before applying the second coat.

2nd COAT

Apply the second coat more sparingly and spread out on the surface with a brush after 5 to 10 minutes. On sidings, windows frame or other surfaces, a third coat is recommended; use the same process as the second coat.

CLEANING

We recommend washing the terraces every year with GLOUROS 1806.

IMPORTANTBEFORE STARTING APPLICATION

As our products are coloured using natural pigments, there may be colour variations between batches. Therefore, it's essential to make a test on a small surface before completing your project. Make sure the result matches your expectation before proceeding.

Moreover, the wood preparation and it's age may also influence colour absorption, and final results may vary accordingly. We are not responsible for the final colour obtained in the event no test were performed or if multiple coloured oils were blended.

THE RESPONSIBILITY OF THE DISTRIBUTOR AND THE MANUFACTURER IS LIMITED TO THE VALUE OF THE PRODUCT.

WARNINGS

TO AVOID SPONTANEOUS COMBUSTION RISKS, RAGS, POLISHING DISCS AND OIL IMPREGNATED APPLICATOR PADS MUST BE PLACED IN A METALLIC SEALED CONTAINER OR SUBMERGED IN WATER BEFORE THEIR DISPOSAL.

version 1